



Clear Concrete Coating

Starting Point Formulation

<u>Materials</u>	<u>Pounds</u>
EXPSF2600	620.00
Dynol 604	4.40
Preblend water and solvent, then add.	
Water	352.20
Dowanol PPH	18.20
BYK 028	5.20
TOTAL:	1000.00

Formulation Attributes

Solids, % by weight	25%
pH	8.0
Viscosity (CPS)	<50
VOC	70.8 g/L
Wt/gal	8.68 lbs./gal.

Chemical Resistance Properties

1 Hour Test, 1 Hour Recovery

Pickle Juice	No Effect
Vinegar	No Effect
Red Wine Vinegar.....	Slight Staining
Mustard	Slight Yellowing, Fades Away